

International Application No.: PCT/JP2005/010639
U.S. Patent Application No.: Unknown
January 11, 2006
Page 3 of 8

IN THE ABSTRACT:

Please replace the Abstract of the Disclosure originally filed with the above-identified patent application with the following new Abstract of the Disclosure:

ABSTRACT OF THE DISCLOSURE

A titanium alloy part has a compressive stress of approximately 270 MPa or more within a depth of about 100 μm from a surface thereof. Since a large compressive stress exists in the area of the surface, the titanium alloy part exhibits a high fatigue strength.